

材料及工程實驗室-台中

試驗報告

報告編號:TV-08-01556X

數: 1 OF 1

報告日期: 97年 08 月 19 日

廠 商: 莹芳實業股份有限公司 託

商: 瑩芳實業股份有限公司 請 廠

料 商: 瑩芳實業股份有限公司 廠

述: EPE FOAM 敘

刑 號: -----

色: -----顏

廠 商: 瑩芳實業股份有限公司 送

期: 97年 08月 05日 日

試 期: 97年 08月 05日~97年 08月 19日 日

註: 以上資料由送驗人員提供(試驗日期除外)

試驗方法:

JIS A9511-2006 (燃燒性試驗-B法)

測試結果:

燃燒試驗

試驗項目	試驗結果					規範要求
	No.1	No.2	No.3	No.4	No.5	
試片原長度(mm)	149.0	149.0	149.0	150.0	149.0	
燃燒時間+燃餘時間(sec)	60	61	62	60	61	120 以下
燃燒剩餘長度(mm)	113.0	114.0	110.0	113.0	112.0	
燃燒長度(mm)	36	35	39	37	37	60 以下

註:試樣接觸火焰燃燒時間:60sec

000

本報告若有提供規範值時,該規範值僅供參考,合格之判定以委託單位實際要求為準。

Unless otherwise stated the results shown in this test report refer only to the sample(s) tested. This test report cannot be reproduced, except in full, without prior written permission of the Company. 除非另有說明,此報告結果僅對測試之樣品負責。本報告未經本公司書面許可,不可部份複製。

This Test Report is issued by the Company under its General Conditions of Service printed overleaf or available on request and accessible at http://www.sgs.com/terms_and_conditions.htm. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this Test Report is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.

TW 6665844